PATENT SPECIFICATION

1 598 738 (11)

(21) Application No. 24172/80 (22) Filed 27 Jan. 1978

(62) Divided out of No. 1598737

(31) Convention Application No. 766926 (32) Filed 9 Feb. 1977 in

(33) United States of America (US)

(44) Complete Specification Published 23 Sep. 1981

(51) INT. CL.³ B31B 23/00 B65D 30/02

(52) Index at Acceptance B8K 2K1 WC



(54) A RECEPTACLE FORMED FROM A TUBULARLY-FORMED SHEET OF A THERMO-PLASTIC MATERIAL

(71) We, BIAX-FIBERFILM CORPORATION, a corporation organized and existing under the laws of the State of Wisconsin, United States of America, of 1066 American Drive, Neenah, Wisconsin, United States of America, do hereby declare the invention, for which we pray that a patent may be granted to us, and the method by which it is to be performed, to be particularly described in and by the following statement:

This invention relates to a receptacle formed from a tubularly-formed sheet of thermoplastic material heated sealed at an end thereof.

Thermoplastic bags for diverse use, such as sandwich bags, garbage bags, leaf bags and the like, are produced by extruding a tube of thermoplastic material, such as high density polyethylene, with the resulting tubularly-formed material being cooled, heat sealed and either scored or cut to the desired length. The thus formed bag exhibits a strip tensile breaking length representative of the processed thermoplastic material. The end use of the thermoplastic bag normally dictates the selection of the thermoplastic material, e.g. as a sandwich bag, a low porosity and normal strength thermoplastic material is selected whereas a garbage bag would require the selection of a thermoplastic material exhibiting high strength characteristics.

The invention provides a receptacle comprising a cylindrically-shaped wall formed of stretched orientable polymeric material heat sealed at an end thereof; said wall being characterized by a strip tensile breaking length of at least twice the strip tensile breaking

length of non-stretched orientable polymeric material.

In a receptacle according to the invention the stretched polymer is preferably bi-axially

stretched.

An advantage of the present invention is that it makes it possible to provide a receptacle formed by bi-axially stretching a collapsed heat-sealable and tubularly-formed sheet or web 25 of thermoplastic material producing a bag having an improved strip tensile breaking strength of at least twice that of the tubularly-formed sheet of thermoplastic material being treated; in effect, providing a significant and unexpected result in that both the heat seal area and the fold area increase in strength, in addition to the film area.

The invention will be more clearly understood by reference to the following detailed description of an exemplary embodiment thereof in conjunction with the accompanying drawings wherein:

Figure 1 is a schematic side elevational view of the apparatus and process of the present

invention; and Figure 2 is a schematic top elevational view of the apparatus and process of the present

invention.

Drive and support assemblies, timing and safety circuits and the like, known and used by those skilled in the art, have been omitted in the interest of clarity.

Referring to Figure 1, there is illustrated a preferred embodiment of the process and apparatus of the present invention including a circular blown film die assembly and a stretching assembly, generally indicated as 10 and 12, respectively. The circular blown film die assembly 10 forming the blown film 12 may be any one of the types of assemblies sold by the Sterling Extruder Corporation of South Plainfield, New Jersey. The blown film 12 is passed about the roller 14 to form a flat two-layered sheet 16 prior to introduction into the heat sealing assembly, generally indicated as 18, as known and used by those skilled in the art, wherein the two layered sheet is heat sealed at selected intervals on a line perpendicular

40

10

20

25

30

35

15

30

10

15

20

25

30

35

40

45

50

55

60

to the movement of the sheet 16.

The thus heat-sealed, two-layered sheet 20 is coursed in a first station, generally indicated as "I" between a nip 22 of a pair of rollers 24 having a plurality of grooves 26 perpendicularly formed to the axis of the rollers 24, as seen in Figure 2. The sheet 20 is maintained against the lower grooved roller 24 by a pair of press rollers 28 to hold the sheet 20 against the lower roller 28 to thereby prevent the sheet 20 from narrowing prior to introduction. Once in the nip 22, the sheet 20 assumes the shape of the groove pattern and becomes stretched by a factor of the draw ratio as hereinafter more clearly described.

In the first station, in effect, lateral stretching, the sheet 20 is wound up at about the same velocity as the feed velocity. The crimp pattern is flattened out by stretching the sheet 20 laterally, such as by means of tenter clamps or curve Mount Hope rolls, generally indicated as 32, such as known and used by one skilled in the art.

The grooves 26 of the rollers 24 are intermeshed like gears, as known to those skilled in the art. As the sheet 20 enters the nip 22, the sheet 20 assumes the shape of a groove 26 and is stretched by a factor determined by the length of the sinus wave " ℓ " of the groove divided by the original length of the web " ω " between contact points of each respective groove tip as disclosed in British Patent Specification No. 1,521,183.

The draw ratio ℓ/ω is calculated by the following equation where

 $a = \pi d/2 \omega,$

and the sinus wave of the groove is

 $\ell/\omega = \int_{0}^{\pi} \sqrt{\frac{1 + a^2 \cos^2 x}{\pi}} dx$

Thus for d/ω ratios of 1.0, 0.75 and 0.5 the draw ratios are 2.35, 2.0 and 1.6, respectively. A laterally stretched sheet 34 is passed from the rollers 32 and is coursed between a nip 40 of a first pair of rollers 42 of a second station "II" with said rollers 42 having a plurality of grooves 44 parallel to the axis of the rollers 42. The sheet 32 is maintained against the lower grooved roller 42 by a pair of press rollers 46 to ensure that the velocity V_1 of the sheet 32 is substantially identical to the surface velocity V_1 of the grooved rollers 42. The grooves 44 of

the rollers 42 are intermeshed like gears, as known to those skilled in the art. As the sheet 34 enters the nip 40, the sheet 34 assumes the shape of a groove 44 and is stretched by a factor determined by the length of the sinus wave "\ell" of the groove divided by the original length of the web "\omega" between contact points of each respective groove tip, as hereinabove discussed with reference to the passage sheet 20 through station I rollers 24.

The sheet 34, after passage through the nip 40 of the rollers 42, is pulled away by a pair of tension rollers 48 having a surface velocity V_2 greater than the surface velocity of the rollers 42, but not greater than a factor of the draw ratio affected in the nip 40 of the rollers 42.

Accordingly, the length of the sheet 34 is therefore increased by such factor. It is noted that the sheet 34 does not undergo narrowing while being longitudinally stretched or extended, as is the case with conventional roller systems. In a preferred embodiment of the present invention, the sheet 34 is passed through two further pairs of grooved rollers 42 to further stretch lengthwise the sheet 34 which is eventually collected on a roller 50.

The maximum permissible draw ratio can easily be determined by measuring the residual elongation of the thermoplastic material. For best results, the grooves 44 of the rollers 42 should be as fine as possible, with groove distance being increased if heavy basis weight factors are to be oriented. From experience, good results are obtained, if the distance between grooves (in mm) is less than 1.0 times the fabric basis weight (in gram/m²). With the process and apparatus of the present invention, a bag is produced having a much higher strip tensile breaking length (STBL - expressed as meters) than a normal produced blown film bag.

Operation of the process and apparatus is described in the following examples which are intended to be merely illustrative, and the invention is not to be regarded as limited thereto.

		•	
	Example 1 A $7'' \times 7''$ double layer sheet is formed by ext (melt flow rate of 0.5 g/mm) and 10% clay an	ruding a mixture of 90% polypropylene d had the following properties:	
5	thickness 0.050" : 127 micron film basis weight : 125 g/m ² STBL : 3570 m break elongation : 1600%		5
10	break elongation : 1600% initial modulus : 1600 m STBL over sea! : 2560 m STBL over fold : 3050 m		10
15	The bag was heat-sealed and stretched in the apparatus 1.5 times on a lateral direction and 3.3 times on a longitudinal direction (3 passes) to a final dimension of 10.5" wide and 23" long. It was noted that the heat-sealed area also stretched. The stretched bag had the following properties:		15
20	STBL : 23550 m break elongation : 40% initial modulus : 185500 m STBL over seal : 15500 m STBL over fold : 16600 m		20
25	Example II The process of Example I was repeated on a similar $7'' \times 7''$ sheet with heat sealing being effected after stretching vice before with the STBL over seal being 2200 m; i.e. less than the STBL over seal of a bag heat sealed before stretching.		25
30	Example III A $7'' \times 7''$ double layer sheet is formed by extruding a 100% polypropylene (melt flow rate of 6.0 g/10 mm) and had the following properties:		30
35	thickness 0.050" : 150 micron film basis weight : 142 g/m² STBL : 3200 m break elongation : 1400% initial modulus : 14500 m STBL over seal : 14500 m		35
40	STBL over fold : 3040 m The bag was heat-sealed and stretched in the apparatus 1.5 times on a lateral direction and 4.5 times on a longitudinal direction (3 passes) to a final dimension of 10.5" wide and 31.5" long. It was noted that the heat-sealed area also stretched. The stretched bag had the		40
45	following properties: thickness : 25 microns		45
50	basis weight : 21 g/m ² STBL : 35700 m (left) break elongation : 25%	ength)	50


Example IV A 7" × 7" double layer sheet is formed by expolypropylene (melt flow rate of 2.0 g/10mm) following properties: 5	tending a mixture of 95% high density and 5% titanium dioxide and had the	
thickness : 200 microns film basis weight : 170 g/m ² STBL : 3800 m		
break elongation : 1800% initial modulus : 12000 m STBL over seal : 2600 m STBL over fold : 2650 m	10	
The bag was heat-sealed and stretched in the apparatus 2.0 times (2 passes) on a lateral direction and 5.0 times on a longitudinal direction (3 passes) to a final dimension of 14.0" wide and 25" long. It was noted that the heat-sealed area also stretched. The stretched bag had the following properties:		
thickness : 22 microns basis weight : 18 g/m² STBL : 38500 m break elongation : 40% initial modulus : 17500 m	20	
STBL over seal : 28500 m 25 STBL over fold : 30400 m	25	
Thus, it is readily apparent to one skilled in the weight per dimension exhibiting substantially impose readily apparent to one skilled in the art, the improved strip tensile breaking length may be a thermoplastic sheet, preferably heat-sealed, eit grooved rollers or sequentially through such ground reference to the preferred embodiment.	oved strip tensile breaking length. It will at depending on end use, that a bag of roduced by passing a tubularly-formed 30 ner through laterally or longitudinally	
Reference is made to our copending British Patent Application No. 3293/78 (Serial No. 1598737), on which the present application is divided, and which claims a process and apparatus for the bi-axial stretching of a tubularly-formed sheet of orientable, polymeric thermoplastic material for forming into bags. WHAT WE CLAIM IS:		
1. A receptacle comprising a cylindrically-shaped wall formed of stretched orientable polymeric material heat sealed at an end thereof; said wall being characterized by a strip tensile breaking length of at least twice the strip tensile breaking length of non-stretched orientable polymeric material. 2. A receptacle according to claim 1 wherein the polymeric material is stretched in two		
different directions. 3. A receptacle according to claim 2 wherein said directions are parallel and perpendicular, respectively, to the axis of said cylindrical wall. 4. A receptacle as claimed in claim 1 and substantially as described herein with reference to the accompanying drawings.		
50 MICHAEL BURNSIDE 2 Serjeants' Fleet Stre London EC4Y	Inn t	
England. Agents for the A Printed for Her Majesty's Stationery Office, by Croydon Prin	oplicants. 55	

1598738

COMPLETE SPECIFICATION

1 SHEET

This drawing is a reproduction of the Original on a reduced scale



.